TITLE OF THE INVENTION

SEMICONDUCTOR DEVICE AND METHOD OF MANUFACTURING
THE SAME

CROSS-REFERENCE TO RELATED APPLICATIONS

5   This application is based upon and claims the
benefit of priority from the prior Japanese Patent
Application No. 2000-193215, filed June 27, 2000,
the entire contents of which are incorporated herein
by reference.

10   BACKGROUND OF THE INVENTION

The present invention relates to a semiconductor
device using a highly dielectric thin film, i.e., a
thin film having a high dielectric constant, as an
insulating film used as, for example, a gate insulating
15   film, particularly, to a semiconductor device in which
nano-crystals are precipitated in a highly dielectric
thin film and a method of manufacturing the same.

Miniaturization of the MOS transistor proceeds
rapidly nowadays and has arrived at the stage where the
20   gate length of 0.1 μm is near at hand. The progress of
miniaturization is based on the situation that it leads
to a high element operating speed and also to low power
consumption. In addition, miniaturization itself
permits diminishing the area occupied by the element so
25   as to make it possible to mount more elements on the
same chip area. It is considered reasonable to
understand that miniaturization is pursued because it

also satisfies allowing the LSI itself to perform many functions.

However, it is expected that the pursuit of miniaturization will reach a deadlock before the gate length is decreased to 0.1 μm because the reduction in the thickness of the gate insulating film is limited.

It was customary to use SiO_2 for forming the gate insulating film positioned below the gate electrode because SiO_2 satisfies the two characteristics indispensable for the operation of the element: the SiO_2 film only bears a minute stationary charge, and, the interfacial level is not formed between the SiO_2 film and the Si layer of the channel portion. Also, SiO_2 is advantageous in that a thin SiO_2 film can be formed easily with good controllability. Because SiO_2 has a low relative dielectric constant of 3.9, a gate insulating film made of SiO_2 and having a thickness not less than 3 nm is required, to satisfy the performance of next generation transistors with a gate length of 0.1 μm. However, it is expected that, in the gate insulating film having a thickness of this level, an increase in the leakage current between the gate and the substrate, which is caused by the direct tunneling phenomenon of the carrier, will pose a problem. The trade off relationship is an unavoidable problem if SiO_2 is used for forming the gate insulating film.

Under the circumstances, vigorous studies are also

being made in an attempt to avoid the tunneling problem
noted above by using a material having a relative
dielectric constant higher than that of SiO_2. Such
studies are being made on films of metal oxides such as

5   Ta_2O_5 and TiO_2. Since Ta_2O_5 and TiO_2 have a relative
dielectric constant of about 20 and about 90,
respectively, in contrast to 3.9 for SiO_2 as noted
above, it is possible to form the films of Ta_2O_5 and
TiO_2 that are about 5 times and about 20 times as thick

10   as the SiO_2 film, to obtain the same gate capacitance
and, thus, Ta_2O_5 and TiO_2 are considered to be
materials effective in suppressing the tunneling
problem.

However, in the metal oxide/Si structure formed by

15   any of the conventional methods, it is unavoidable for
the polycrystal of the metal oxide to be formed through
the heat treating step carried out at temperatures
higher than 800℃ for forming the transistor. The
problems inherent in the conventional refractory metal

20   oxide thin film thus formed will now be described with
reference to FIG. 1. In FIG. 1, reference numeral 90
denotes a silicon substrate, reference numeral 92
denotes a TiO_2 film, which is a highly dielectric metal
oxide thin film, reference numeral 94 denotes a gate

25   electrode, and reference numeral 95 denotes a grain
boundary.

A first problem inherent in the structure shown in

FIG. 1 is that an electric current is likely to flow through the grain boundary 95 so as to increase the leakage current between the gate and the substrate. A difficulty is considered to be brought about by the fact that the metal-oxygen bond is incomplete in the grain boundary region, compared with the grain region. Also, it is said that, even in the boundary in which a complete bond is once obtained, fatigue tends to occur if an electric current is allowed to flow through the boundary. In other words, an SILC (Stress Induced Leakage Current) tends to flow, which increases the leakage current.

A second problem arising from the generation of the grain boundary in a thin film of a refractory metal is that polycrystalline grains are oriented at random, which renders the effective relative dielectric constant nonuniform. The difficulty is caused by the fact that the microcrystalline highly dielectric material has an anisotropy in its relative dielectric constant ε_r. For example, TiO_2 exhibits a relative dielectric constant ε_r of 89 where an electrode is formed in parallel to the c-axis and exhibits a relative dielectric constant ε_r of 170 where an electrode is formed in a direction perpendicular to the c-axis.

It should also be noted that, where a TiO_2 layer is formed by, in general, a sputtering method or a CVD

method and, then, subjected to a heat treatment at temperatures not lower than 800°C, the grain size within the thin film of the refractory metal falls within a range of between 10 nm and 50 nm. It follows that, in the case of forming a MOS transistor having a gate length Lg of, for example, 30 nm, the threshold voltage V_{th} and the current driving force I_t are rendered nonuniform as shown in FIGS. 2A and 2B depending on the portion of the TiO_2 layer, which is oriented at random, on which the gate electrode is formed. This is a major defect in forming a MOS transistor in an LSI, making it impossible to form a circuit of good characteristics.

BRIEF SUMMARY OF THE INVENTION

As described above, the problems in using a metal oxide for forming a gate insulating film can be summarized as follows.

(1) The leakage current between the gate electrode and the substrate is increased by the leakage current in the grain boundary.

(2) The increase in the leakage current between the gate electrode and the substrate that is induced by the application of the current stress (SILC) is prominent.

(3) The threshold value and the driving force of a very small MOS transistor, which is smaller than 50 nm, are rendered nonuniform, which makes it

difficult to design an LSI.

The present invention, which has been achieved in view of the situation described above, is intended to provide a semiconductor device, which permits suppressing the leakage current derived from the grain boundary, permits suppressing the nonuniformity in the threshold value and the driving force, and also permits improving the characteristics of a MOS transistor, etc. and a method of manufacturing the particular semiconductor device.

The present invention is also intended to provide a semiconductor device, which permits suppressing the leakage current derived from the crystal grain boundary, eliminates trapped charges within the film so as to suppress the nonuniformity in the threshold value and the driving force, and is effective in improving the characteristics of a MOS transistor, etc. and a method of manufacturing the particular semiconductor device.

According to one aspect of the present invention, there is provided a semiconductor device comprising:

a semiconductor substrate, and

a circuit element using an insulating film formed on the semiconductor substrate,

the insulating film containing a silicon compound containing at least one element selected from the group consisting of an oxygen and a nitrogen, and a metal

compound containing a metal other than silicon and at least one element selected from the group consisting of an oxygen and a nitrogen, nano-crystals being formed in the insulating film, the size of the nano-crystal being small enough to permit observation of a polycrystalline ring as a diffraction image when an electron beam having a beam diameter of the nanometer order is incident in parallel to the insulating film surface.

Further, according to another aspect of the present invention, there is provided a method of manufacturing a semiconductor device of the present invention, comprising:

forming an insulating film containing a silicon compound containing at least one element selected from the group consisting of an oxygen and a nitrogen, and a metal compound containing a metal other than silicon and at least one element selected from the group consisting of an oxygen and a nitrogen, on a semiconductor substrate under temperatures at which crystallization does not take place; and

applying a heat treatment to precipitate a nano-crystalline metal oxide within the mixed film.

Further, according to another aspect of the present invention, there is provided a method of manufacturing a semiconductor device of the present invention, comprising:

forming insulating film being a mixed film

including a silicon compound containing at least one
element selected from the group consisting of an oxygen
and a nitrogen, and a metal compound containing a metal
other than silicon and at least one element selected

5   from the group consisting of an oxygen and a nitrogen
on a semiconductor substrate under temperatures at
which crystallization does not take place; and

applying a heat treatment to precipitate a
nano-crystalline metal oxide within the mixed film.

10   BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWING

FIG. 1 is a cross sectional view for explaining
the problems inherent in the prior art;

FIGS. 2A and 2B are graphs for explaining the
problems inherent in the prior art;

15   FIG. 3 is a cross sectional view showing the basic
structure of a semiconductor device according to one
embodiment of the present invention;

FIGS. 4A to 4E are cross sectional views
collectively showing as an example the manufacturing

20   process of a semiconductor device for Example 1 of the
present invention;

FIG. 5 is a graph showing that the leakage current
is suppressed in accordance with an increase in the
silicon content of the gate insulating film;

25   FIG. 6 is a graph showing an estimated
nonuniformity of the threshold value and the effect
of suppressing the nonuniformity produced by the

application of one embodiment of the present invention;

FIG. 7 is a graph showing the relationship between the silicon content of the gate insulating film and the relative dielectric constant;

FIGS. 8A to 8E are cross sectional views collectively showing the manufacturing process of a semiconductor device for Example 3 of the present invention;

FIG. 9 is a cross sectional view showing the construction of an element according to a modification of Example 3 of the present invention;

FIGS. 10A to 10D are cross sectional views collectively showing the manufacturing process of a semiconductor device for Example 4 of the present invention;

FIG. 11 is a cross sectional view schematically showing the nano-crystals within the mixed film;

FIG. 12 is a drawing schematically showing the levels in the thickness direction under the state shown in FIG. 11;

FIGS. 13A to 13C are cross sectional views collectively showing the basic structure of the semiconductor device according to other embodiment of the present invention;

FIGS. 14A and 14B are graphs each showing the dependence of the C-V (capacitance-gate voltage) characteristics on the thickness of the film; and

FIGS. 15A to 15E are cross sectional views collectively showing the manufacturing process of a semiconductor device for Example 6 of the present invention.

DETAILED DESCRIPTION OF THE INVENTION

The present invention will now be described in detail with reference to the accompanying drawings.

One embodiment of the present invention is directed to a semiconductor device in which an insulating film made of a highly dielectric thin film is formed on a semiconductor substrate and is featured in that nano-crystals are precipitated in the insulating film.

FIG. 3 exemplifies a case where the technical idea of one embodiment according to the present invention is applied to a MOS transistor. In the MOS transistor shown in FIG. 3, a gate insulating film 11 containing a highly dielectric thin film and a gate electrode 12 are formed on a semiconductor substrate 10 such as a silicon substrate. It is desirable for the thickness of the gate insulating film 11 containing a highly dielectric thin film to fall within a range of between 3 nm and 20 nm. Further, source-drain regions 13a, 13b are formed on both sides of the gate electrode 12. The gate insulating film 11 may be formed of a mixed film including a silicon compound containing at least one element selected from the group consisting of

an oxygen and a nitrogen, and a metal compound
containing a metal other than silicon and at least one
element selected from the group consisting of an oxygen
and a nitrogen. The entire mixed film is not

5   amorphous, and nano-crystals are formed in the mixed
film.

Very small grains of single crystals are
collectively called nano-crystals. The size of nano-
crystals is about 10 nm or less, for example, and is

10   sufficiently smaller than the gate length Lg.

Whether or not the crystals within the thin
film are nano-crystals are determined as follows.
Specifically, if an electron beam diffraction ED, in
which the diameter of the beam is generally scores of

15   nanometers, is applied to a sample to be measured,
a spot-like diffraction image is obtained in the case
where the sample is a single crystal, and a ring-like
diffraction image (polycrystalline ring) is obtained
in the case where the sample is polycrystalline.

20   It should be noted that, if the diameter of the
electron beam is diminished to a nanometer order (1 nm
to 10 nm), e.g., about 5 nm, the diffraction image
forms a spot even in the case of the polycrystal,
and a polycrystalline ring can be observed in the case

25   of the microcrystal smaller than the polycrystal.
It follows that, in the case of employing electron
beam diffraction using an electron beam having a very

small diameter of about 5 nm, it is possible to determine whether or not the sample to be measured is microcrystalline depending on whether or not the polycrystalline ring can be observed.

5 According to a one aspect of the present invention, there is provided a semiconductor device comprising:

a semiconductor substrate, and

a circuit element using an insulating film formed 10 on said semiconductor substrate,

said insulating film containing a silicon compound containing at least one element selected from the group consisting of an oxygen and a nitrogen, and a metal compound containing a metal other than silicon and at 15 least one element selected from the group consisting of an oxygen and a nitrogen, nano-crystals being formed in said insulating film, the size of said nano-crystal being small enough to permit observation of a polycrystalline ring as a diffraction image when 20 an electron beam having a beam diameter of the nanometer order is incident in parallel to said insulating film surface.

As described above, in the semiconductor device of one aspect of the present invention, nano-crystals, not 25 polycrystals, are precipitated in the gate insulating film containing a highly dielectric thin film. In some cases, an amorphous material enters the grain boundary

in the insulating film included in the semiconductor device of one aspect according to the present invention. It follows that it is possible to suppress the leakage current derived from the grain boundary.

The nano-crystals may be formed in the insulating film, it is preferable that the size of the largest nano-crystal grain in the insulating film being not larger than the thickness of the insulating film.

The size of the nano-crystal is smaller than the width W of the gate insulating film and is sufficiently smaller than the gate length Lg. When the size of the largest nano-crystal grain in the insulating film is defined to be smaller than the thickness of the insulating film, it is impossible for the grain boundary to extend through the front and back surfaces of the film. Since a plurality of nano-crystals are present in the longitudinal direction of the gate, it is also possible to suppress the nonuniformity in the threshold value and the driving force.

In the semiconductor device according to any of the embodiments of the present invention, it is desirable for nano-crystal grains of an oxide, a nitride or an oxynitride of a metal other than silicon to be dispersed in the gate insulating film in order to obtain a high dielectric constant.

The insulating film may be a mixed film including a silicon compound containing at least one element

selected from the group consisting of an oxygen and a nitrogen, and a metal compound containing a metal other than silicon and at least one element selected from the group consisting of an oxygen and a nitrogen.

Where a mixed film containing titanium oxide and silicon oxide is used as the gate insulating film, the leakage current is diminished and the dielectric constant is increased with an increase in the silicon content of the mixed film. It follows that it is desirable for the gate insulating film to be formed of a mixed film containing titanium oxide and silicon oxide. The particular mixed film can be formed by a sputtering method using a mixed sintered body containing titanium oxide and silicon oxide used as a target. According to the experiment conducted by the present inventors, the leakage current can be sufficiently lowered and the relative dielectric constant is increased to a level not lower than 50, if the silicon content of the mixed film is not lower than 15%. It follows that it is desirable for the average silicon content of the mixed film, i.e., the value of Si/(Si + Ti), to be not lower than 15%.

As described above, it is desirable for the average silicon content of the mixed film, i.e., the value of Si/(Si + Ti), to be not lower than 15%. In this case, the effect produced by nano-crystallization is further improved. Further, it is desirable for the

silicon content, i.e., the value of Si/(Si + Ti), to be

not higher than 80%. In this case, it is possible to

obtain a relative dielectric constant ε_r, which is

larger than 10, required for the highly dielectric

5   film. It is more desirable for the silicon content,

i.e., Si/(Si + Ti), to fall within a range of between

15% and 60%. In this case, it is possible to obtain a

high relative dielectric constant.

It is desirable for the particle diameter of the

10   nano-crystal within the mixed film to be not larger

than 10 nm, more preferably, to fall within a range of

between 1 nm and 10 nm. In this case, it is possible

to suppress the nonuniformity in the threshold value

and the driving force of the very small MOS transistor

15   that is sized smaller than 50 nm.

The insulating film included in the semiconductor

device of one embodiment of the present invention can

be formed by forming on a semiconductor substrate a

mixed film containing at least one material selected

20   from the group consisting of silicon oxide, silicon

nitride and silicon oxynitride and at least one

material selected from the group consisting of an

oxide, a nitride and an oxynitride of a metal other

than silicon under temperatures at which the

25   crystallization does not take place, followed by

applying a heat treatment to the resultant mixed film

so as to permit the nano-crystalline metal oxides to

precipitate in the mixed film.

It is desirable for the heat treatment for precipitating the nano-crystalline metal oxides to be carried out at a pressurized atmosphere higher than the atmospheric pressure of room temperature, i.e., under a pressurized atmosphere higher than 100 kPa. In this case, it is possible to suppress the diameter of the nano-crystals to a level not larger than several nanometers.

It is desirable to decrease the thickness of the insulating film by partly etching the nano-crystals precipitated by the heat treatment.

Further, it is desirable to form, before formation of the mixed film, a thin film for preventing oxidation on the underlying substrate, e.g., a silicon substrate. To be more specific, it is desirable to form an oxynitride film by a heat treatment using, for example, a NO gas.

As described above, in one embodiment of the present invention, a highly dielectric thin film formed of a mixed film containing at least one material selected from the group consisting of silicon oxide, silicon nitride and silicon oxynitride and at least one material selected from the group consisting of an oxide, a nitride and an oxynitride of a metal other than silicon is used as a gate insulating film, and nano-crystals are precipitated in the thin film.

The particular construction of one embodiment of
the present invention makes it possible to suppress the
leakage current derived from the grain boundary and to
suppress the nonuniformity in the threshold value and
the driving force. It follows that it is possible to
improve the characteristics of the MOS transistor, etc.
Example 1:

FIGS. 4A to 4E are cross sectional views
collectively showing the manufacturing process of
a semiconductor device for Example 1 of the present
invention.

The processes shown in FIGS. 4A to 4E and in
FIGS. 8A to 8E, 9 and 10A to 10D referred to herein
later are directed to n-channel MOSFETs. However,
the present invention is not limited to an n-channel
MOSFET. As a matter of fact, it is possible for
a p-channel MOSFET to be formed together on the same
substrate, and the present invention is described
herein later bearing in mind that the p-channel MOSFET
is formed by the same process. Therefore, it is
assumed that the silicon substrate is doped with a
p-type impurity unless otherwise specified. Of course,
the technical idea of the present invention can be
applied to an SOI (Silicon On Insulator) MOSFET and a
vertical MOSFET in which the channel region extends in
a direction perpendicular to the substrate surface and
the electrons and holes are migrated in a direction

perpendicular to the substrate surface.

In the first step, a SiO_2 film 21 for the trench element isolation is formed on a p-type silicon substrate 20, followed by depositing a mixed film 22 of TiO_2/SiO_2 on the entire surface under temperatures at which crystallization does not take place, e.g., at room temperature, as shown in FIG. 4A. The mixed film 22 can be deposited by any of a vapor deposition method, an ordinary RF sputtering method, a sputtering method using a helical coil, a sol-gel method, a laser ablation method and a CVD method. Naturally, the temperature and the forming conditions of the mixed film 22 differ depending on the method of depositing the mixed film 22.

In Example 1, the mixed film 22 was deposited by a sputtering method. To be more specific, a target is prepared by finely pulverizing TiO_2 and SiO_2, followed by sintering the pulverized materials mixed at a predetermined mixing ratio. The mixing ratio of $Si/(Ti + Si)$ is set at 20%. After the target is positioned to face the silicon substrate, a sputtering was performed for 30 minutes under a mixed gas atmosphere of Ar and O_2 (Ar: 20 sccm; O_2: 2 sccm) so as to deposit the mixed film 22 in a thickness of 20 nm. The sputtering was performed at room temperature with the power set at 100 W.

In the next step, a heat treatment was applied to

the mixed film 22 at 800℃ for 30 seconds under an Ar gas atmosphere so as to convert the mixed film 22 into a highly dielectric film 23 containing nano-crystals, as shown in FIG. 4B.

Then, a patterned gate electrode 24 and a patterned highly dielectric insulating film 23 are obtained as shown in FIG. 4C. The gate electrode 24 and the highly dielectric insulating film 23 can be formed as follows. In the first step, a metal silicide film, e.g., a SiGe film 24, is deposited in a thickness of 100 nm as the gate electrode at 550℃ under a mixed gas atmosphere containing SiH_4 and GeH_4. Then, a resist pattern is formed by photolithography, followed by performing an acidic ion etching by using the resultant resist pattern as a mask under an atmosphere of $CF_4 + O_2$ so as to process the SiGe film 24 into the shape of a gate electrode. Then, the highly dielectric insulating film 23 containing the nano-crystals is processed by using a solution containing HF.

Further, an As ions are implanted with a dose of 1×10^{14} cm^{-2} under an accelerating energy of 300 eV by using the SiGe film 24 as a mask, as shown in FIG. 4D. Then, a SiN film is deposited on the entire surface, followed by etching back the SiN film on the entire surface by RIE so as to form a gate side wall SiN film 25 in a thickness of 10 nm. Further, As ions are implanted again at a dose of 1×10^{15} cm^{-2} under

an accelerating energy of 10 keV with the SiGe film 24

and the SiN film 25 used as a mask. Still further,

an RTA (rapid temperature annealing) is applied at

a temperature between 900℃ and 1200℃ for about 1 to

5   30 seconds so as to form source-drain regions 26a, 26b

and to add an n-type impurity to the SiGe film 24

forming the gate electrode.

Then, a $CoSi_2$ film 27 is deposited on each of the

source region, the drain region and the gate electrode

10   by deposition of Co/heat treatment/etching, as shown

in FIG. 4E. Finally, a SiO_2 film 28 acting as an

interlayer insulating film is deposited on the entire

surface by using, for example, TEOS, followed by making

contact holes communicating with the source-drain

15   regions in the SiO_2 layer 28. Further, a wiring layer

29 of Al/TiN/Ti or Cu/TiN/Ti is formed to fill the

contact holes. In the subsequent process, the steps

for forming the second wiring layer et seq. are carried

out so as to finish the manufacture of an LSI.

20   In this Example 1, nano-crystals in the highly

dielectric insulating film 23 are formed immediately

after depositing the mixed film. However, it is

possible to form the nano-crystals after depositing

the gate electrode or after patterning the highly

25   dielectric insulating film. Alternatively it is also

possible to form the nano-crystals during activating

the impurity doped in the semiconductor substrate.

FIG. 5 is a graph showing the change in the leakage current through the TiSiO film having a thickness of 100 nm relative to the silicon content of the mixed film. As apparent from the graph, the

5 leakage current is decreased with increase in the silicon content to exceed 15%. The decrease in the leakage current is brought about because the TiSiO film, which is columnar under the polycrystalline state as shown in FIG. 1, is formed of nano-crystals of the

10 nanometer order in the case where the silicon content is not lower than 15%. The present inventors have confirmed the particular phenomenon by observation with an electron microscope of high resolution.

FIG. 6 shows the estimated nonuniformity of the

15 threshold voltage, which was calculated in respect of two crystal grain diameters of TiO_2. Where the size of the gate electrode is diminished, the threshold value is made widely nonuniform to fall within a range of between 0.12 V and 0.36 V in the case of using a film

20 formed of ordinary crystal grains having a grain diameter of 50 nm. On the other hand, FIG. 6 shows that, where the crystal grain diameter is decreased to 5 nm, the nonuniformity of the threshold value is narrowed to fall within a range of $0.24V \pm 0.04V$. This

25 supports that the influence of the anisotropy in the relative dielectric constant owing to the direction of the crystal axis of TiO_2 is suppressed by the

miniaturization of the crystal grains.

The present inventors have also found through extensive research, that the TiO_2/SiO_2 mixed film formed of nano-crystals exhibits a very high relative dielectric constant in the case where the silicon content of the mixed film is not lower than 15%. This is highly effective for the manufacture of the next generation LSIs, i.e., an LSI having a gate length Lg of 10 nm, in that it is possible to increase the capacitance between the gate and the substrate while suppressing the leakage current, i.e., power consumption of the LSI.

As described above, in Example 1, a TiO_2/SiO_2 mixed film containing 20% of silicon is used as the gate insulating film 23, and nano-crystals are precipitated in the mixed film. Further, an amorphous material enters the grain boundary, with the result that it is possible to suppress the leakage current derived from the grain boundary. It should also be noted that, since a plurality of nano-crystals are present in the longitudinal direction of the gate, it is possible to suppress the nonuniformity in the threshold value and the driving force even in a very small MOS transistor sized not larger than 50 nm. Further, it has also been found possible to suppress the SILC after application of the current stress.

Example 2:

Example 2 is a modification of Example 1
and differs from Example 1 in the step of forming
the nano-crystals. The manufacturing process of
the semiconductor device for Example 2 can be described
with reference to FIGS. 4A to 4E referred to previously
in conjunction with Example 1.

In the first step, the structure shown in FIG. 4A
is obtained by depositing, by the method similar
to that described previously in conjunction with
Example 1, a mixed film 22 containing a TiO_2 and SiO_2
on a p-type silicon substrate 20 having a SiO_2 film 21
for the element isolation formed therein under
temperatures at which crystallization does not take
place.

Then, in the step shown in FIG. 4B, a highly
dielectric insulating film 23 containing nano-crystals
was formed under a lower temperature by applying a heat
treatment at 600℃ for 30 seconds under a high pressure
of 10 MPa. By forming the highly dielectric insulating
film 23 under a low temperature, it is possible to
suppress the diffusion of the impurity in the channel
region and to make finer the nano-crystals within the
highly dielectric insulating film 23. The subsequent
steps are equal to those for Example 1, which are shown
in FIGS. 4C to 4E, thereby manufacturing an LSI.

Example 2 also produces the effects similar to

those produced by Example 1 described previously.

In addition, in Example 2, it is possible to suppress
the diffusion of the impurity so as to make finer the
crystal grains of the nano-crystals because the heat
treatment for forming the nano-crystals is carried out
under a high pressure. According to the experiment
conducted by the present inventors, the particular
effects can be produced if the pressure in the heat
treating step is set at 100 kPa or higher.

Example 3:

FIGS. 8A to 8E are cross sectional views
collectively showing the manufacturing process of the
semiconductor device for Example 3. Reference numerals
60 to 69 shown in FIGS. 8A to 8E correspond to
reference numerals 20 to 29 shown in FIGS. 4A to 4E,
respectively.

In the first step, a mixed film 62 containing TiO_2
and SiO_2 is deposited on a p-type silicon substrate 60
having a SiO_2 film 61 for the element isolation formed
therein in advance under temperatures at which
crystallization does not take place. This step is
equal to that for Example 1. In Example 3, however,
the mixed film 62 has a large thickness of 100 nm.

In the next step, a heat treatment was applied at
800°C for 30 seconds under an Ar gas atmosphere so as
to convert the mixed film 62 into a highly dielectric
insulating film 63 containing nano-crystals of TiO_2, as

shown in FIG. 8B. Then, the thickness of the highly dielectric insulating film 63 was decreased to 20 nm by the treatment with a solution containing HF, e.g., a mixed solution containing 1 part of a 47% HF and

5   10 parts of H_2O, for 5 minutes, as shown in FIG. 8C. It is also possible to decrease the thickness of the highly dielectric insulating film 63 before the heat treatment for forming the nano-crystals.

Further, a gate electrode of, for example, a SiGe

10   film 64 was deposited by a CVD method in a thickness of 100 nm, followed by processing the SiGe film 64 by photolithography into the shape of the gate electrode, as shown in FIG. 8D. Still further, a gate side wall SiN film 65 was formed, followed by forming source-

15   drain regions 66a, 66b as in Example 1.

In the subsequent steps, a SiO_2 film 68 acting as an interlayer insulating film was formed on the entire surface, followed by making contact holes in the SiO_2 film 68 and subsequently forming a wiring layer 69 of

20   Al/TiN/Ti or Cu/TiN/Ti structure as in Example 1 so as to finish manufacture of a MOS transistor, as shown in FIG. 8E.

The etch back step of the highly dielectric insulating film 63 containing nano-crystals, which was

25   employed in Example 3, can also be applied to the case other than the case where the etch back is performed uniformly over the entire surface. It is possible to

apply the etch back to only a part, e.g., to only

the p-channel MOS, to only the portion corresponding to

the logic SLI in a mixed LSI, or to only the portion

corresponding to the memory LSI.

5   FIG. 9 is a cross sectional view showing the

construction of an element in which an n-channel MOSFET

and a p-channel MOSFET are arranged on the same

substrate. Reference numeral 700 shown in FIG. 9

denotes a silicon substrate, reference numeral 701

10   denotes an element isolating insulating film, reference

numeral 708 denotes an interlayer insulating film,

reference numeral 709 denotes a wiring layer, reference

numeral 710 denotes a p-type well, reference numeral

720 denotes an n-type well, each of reference numerals

15   713 and 723 denotes a gate insulating film, each of

reference numerals 714 and 724 denotes a gate

electrode, each of reference numerals 716 and 726

denotes source-drain regions. As apparent from the

drawing, the members 710 to 716 referred to above

20   collectively form an n-channel MOSFET, and the members

720 to 726 referred to above collectively form

a p-channel MOSFET.

The etch back of the highly dielectric insulating

film containing nano-crystals is applied to only the

25   n-channel MOSFET region in the following case. Where

the work function of the gate electrode is on the

side of the valence band relative to the intrinsic

Fermi level Ei of the band gap of Si, the threshold
value $|V_{thn}|$ of the n-channel is rendered larger than
the threshold value $|V_{thp}|$ of the p-channel, with the
result that the timing of the CMOS logic is rendered

5   unbalanced.

In this case, it is possible to diminish the
threshold value $|V_{thn}|$ of the n-channel so as to
moderate the unbalance by decreasing the thickness of
the gate insulating film on the side of only the

10 n-channel of the n-channel MOSFET. Of course, where
the work function of the electrode is on the side of Ec
relative to Ei, the thickness of the gate insulating
film on the side of the p-channel is decreased. On the
other hand, it is conceivable to decrease the thickness

15 of the gate insulating film in a logic LSI requiring
a high speed operation and to use a thick film in
a memory LSI in which the leakage current is
preferentially minimized.
Example 4:

20   FIGS. 10A to 10D are cross sectional views
collectively showing the manufacturing process of a
semiconductor device for Example 4 of the present
invention. Incidentally, reference numerals 80 to 89
shown in FIGS. 10A to 10D correspond to reference

25 numerals 20 to 29 shown in FIGS. 4A to 4E,
respectively.

In the first step, a SiO_2 film 81 for the element

isolation is formed on a p-type silicon substrate 80,
followed by an ion implantation for controlling the
threshold value of the MOS transistor, as shown in
FIG. 10A. Then, after the oxide film other than the
SiO$_2$ film 81 is completely removed, a heat treatment is
applied at 850℃ for 5 seconds using a NO gas so as
to form an oxynitride film 802 having a thickness of
0.7 μm, followed by forming a mixed film 82 of a
TiO$_2$/SiO$_2$ structure. Since the oxynitride film 802 is
formed on the silicon substrate 80 as shown in
FIG. 10A, a further oxidation of the surface of the
silicon substrate is suppressed even if a sputtering is
performed under an atmosphere containing O$_2$.

In the next step, a highly dielectric insulating
film 83 containing nano-crystals of TiO$_2$ is formed by
a heat treatment at 800℃ for 30 seconds under an Ar
atmosphere, as shown in FIG. 10B. In the subsequent
process, the formation of the gate electrode 84 and
the side wall SiN film 85, the ion implantation for
forming the source-drain regions, and the formation of
an interlayer insulating film 88 and a wiring layer 89
are carried out as in Example 1, as shown in FIGS. 10C
and 10D, thereby finishing the manufacture of an LSI.

In this Example 4, nano-crystals in the highly
dielectric insulating film 83 are formed immediately
after depositing the mixed film. However, it is
possible to form the nano-crystals after depositing

the gate electrode or after patterning the highly
dielectric insulating film. Alternatively it is also
possible to form the nano-crystals during activating
the impurity doped in the semiconductor substrate.

5   FIG. 11 schematically shows the nano-crystals in
the case of using the mixed film defined in one example
of the present invention. Reference numeral 152 in
FIG. 11 denotes the nano-crystal, and reference numeral
153 denotes the mixed film. The mixed film 153

10   containing these nano-crystals 152 can be formed by
forming a mixed film in a thickness of about 100 nm by
a sputtering method using a mixed sintered body of TiO_2
and SiO_2 as a target, followed by an annealing
treatment at 800°C for 30 seconds under an Ar gas

15   atmosphere. In the annealing step, the nano-crystals
152 of TiO_2 are precipitated. It is possible to
decrease the grain diameter of the TiO_2 crystal grains
by increasing the SiO_2 concentration in the mixed
film 153. It follows that it is possible to suppress

20   the nonuniformity in the threshold value dependent on
the anisotropy of ε_r referred to previously and in the
current driving force in the case of forming a MOS
transistor having a gate length Lg of 30 nm. It is
also possible to suppress the leakage current flowing

25   through the crystal grain boundary by increasing the
SiO_2 concentration.

However, it has also been clarified by further

research conducted by the present inventors that the
trapping of electric charge tends to take place easily
in the mixed film containing the nano-crystals, which
possibly invites the problem of fluctuation in the

5   threshold value of the MOSFET and deterioration in the
reliability of the gate insulating film. The trapping
of the electric charge is derived from the fact that
the energy level of the TiO_2 nano-crystal 152 is lower
than that of the peripheral region, in which the

10 silicon oxide is contained in a large amount, of the
nano-crystal 152. To be more specific, where the size
of the TiO_2 nano-crystal 152 in the thickness direction
of the mixed film 153 is smaller than the thickness
of the mixed film 153, the energy level of the TiO_2

15 nano-crystal is lower than that in the peripheral
region so as to form a quantum well. The electrons are
trapped in the quantum well. It is also conceivable
for the holes to be trapped in the quantum well.

   FIG. 12 schematically shows the energy levels in

20 the thickness direction in the TiO_2 nano-crystal 152
and the mixed film 153 around the nano-crystal 152.
The particular phenomenon is considered to take place
not only in TiO_2 but also in a mixed film containing
a highly dielectric metal oxide and silicon oxide that

25 are subjected to phase separation after the heat
treatment.

   The present inventors have found that, in order to

prevent the electric charge from being trapped in the insulating film containing nano-crystals, it is effective for a part of the periphery of at least one of the nano-crystals to be positioned within a distance of 0.7 nm from the interface with the insulating film.

To be more specific, in another embodiment of the present invention, a part of the periphery of at least one of the nano-crystals may be positioned within a distance of 0.7 nm from the interface of the insulating film.

FIGS. 13A to 13C collectively show a MOS transistor to which the technical idea of another embodiment of the present invention is applied. In the MOS transistor shown in FIGS. 13A to 13C, a gate insulating film 113 containing a highly dielectric film and a gate electrode 114 are formed successively on a semiconductor substrate 110 such as a silicon substrate. Further, source-drain regions 116a, 116b are formed on both sides of the gate electrode 114. It should be noted that the gate insulating film 113 may be a mixed film including a silicon compound containing at least one element selected from the group consisting of an oxygen and a nitrogen, and a metal compound containing a metal other than silicon and at least one element selected from the group consisting of an oxygen and a nitrogen. The entire region of such a mixed film is not amorphous, and a large number of nano-crystals

112 are precipitated in the mixed film. In the
embodiment of the present invention, it is most
desirable for the nano-crystals to be formed in a
manner to extend through the front and back surfaces of
5   the mixed film 113. However, it is not absolutely
necessary for all the nano-crystals to extend through
the front and back surfaces of the mixed film 113. It
suffices for a major portion of the nano-crystals to
extend through the front and back surfaces of the mixed
10   film 113. To be more specific, it is possible to
obtain a sufficient effect if at least 50% by volume of
the nano-crystals are formed in a manner to extend
through the front and back surfaces of the mixed
film 113.

15   As described previously, very small single
crystals are collectively called nano-crystals. To be
more specific, the nano-crystal is not larger than
about 10 nm and is sufficiently smaller than the gate
length Lg of the MOSFET. Whether or not the crystals
20   in the thin film are nano-crystals can be determined by
an electron beam diffraction, as described previously.

            Where a mixed film containing titanium oxide and
silicon oxide is used as the gate insulating film,
the leakage current can be diminished and the relative
25   dielectric constant of the mixed film can be increased
with an increase in the silicon content of the film, as
described previously. It follows that it is desirable

for the mixed film to be a mixed film containing

titanium oxide and silicon oxide. The particular

mixed film can be formed by a sputtering method with

a sintered body containing titanium oxide and silicon

5   oxide used as a target. The present inventors have

experimentally confirmed that, if the silicon content

of the mixed film is increased to 15% or more,

the leakage current can be sufficiently lowered and

the relative dielectric constant is increased to 50

10   or more. It follows that it is desirable for

the silicon content of the mixed film, i.e., the value

of Si/(Si + Ti), to be not lower than 15%.

As described above, it is desirable for the

silicon content of the mixed film, i.e., the value of

15   Si/(Si + Ti), to be not lower than 15%. In this case,

the effect produced by the nano-crystallization can

be enhanced. It is more desirable for the value of

Si/(Si + Ti) to be not higher than 80%. In this case,

it is possible to obtain the relative dielectric

20   constant ε_r larger than 10, which is required for

a highly dielectric film. It is further more desirable

for the value of Si/(Si + Ti) to fall within a range of

between 15% and 60%. In this case, it is possible to

obtain a further higher relative dielectric constant.

25   As explained by quantum theory, where Si is

brought into contact with SiO_2, the wave function of Si

oozes into SiO_2 by about 0.7 nm (D.A. Muller et al.,

NATURE, 399 (1999) 758). It follows that, where the
gate electrode is formed of polycrystalline silicon
(polysilicon), it is possible for the TiO_2 crystal
grains to be surrounded by a SiO_2 layer having a

5 thickness of about 0.7 nm in a mixed film in which
a material having an energy level lower than that of
the main medium of SiO_2, e.g., TiO_2 crystal grains, is
precipitated in the SiO_2 layer. FIG. 13B shows the
construction in such a case. Further, in a MOS device,

10 no problem is generated even if a main interfacial
layer of SiO_2 is formed at the interface between the
silicon substrate and the gate insulating film or at
the interface between the gate electrode and the gate
insulating film, as long as the thickness of the main

15 interfacial layer of SiO_2 is not larger than the value
noted above. FIG. 13C shows the construction for such
a case.

Incidentally, where the material of the gate
electrode and the substrate is not silicon or where the

20 mixed film contains materials other than TiO_2 and SiO_2,
the oozing length of the wave function also differs.
For example, if SiO_2 is replaced by a material having
a lower energy level, the oozing length of the wave
function of silicon is rendered large. In this case,

25 the distance between the nano-crystal and the interface
of the mixed film is not limited to a range not larger
than 0.7 nm and can be increased in accordance with the

oozing length of the wave function.

As described above, in the another embodiment of the present invention, the crystals precipitated in the gate insulating film formed of a highly dielectric film are not polycrystals but single crystals and are sufficiently smaller than the gate length Lg. Also, an amorphous material enters the crystal grain boundary. As a result, it is possible to suppress the leakage current derived from the crystal boundary. In addition, a plurality of nano-crystals are present in the longitudinal direction of the gate, and the size of the nano-crystal is substantially equal to the width W of the mixed film such that crystal boundary extends through the front surface and the back surface of the film. It follows that it is possible to markedly decrease the trap density that is dependent on the energy level of the nano-crystal present in the mixed film. In order to obtain a high dielectric constant, it is desirable for at least the nano-crystals of a metal oxide to be dispersed in the gate insulating film.

The semiconductor device shown in FIGS. 13A to 13C is equal to that shown in FIG. 3, except that a part of the periphery of at least one of the nano-crystals dispersed in the gate insulating film is present within a distance of 0.7 nm from the interface of the insulating film.

The insulating film in the particular semiconductor device can be formed as follows. Specifically, in the first step, a mixed film containing at least one of silicon oxide, silicon nitride and silicon oxynitride and at least one of an oxide, a nitride and an oxynitride of a metal other than silicon is formed on a semiconductor substrate under a temperature at which crystallization does not take place. Then, a heat treatment is applied so as to precipitate a plurality of nano-crystals of the metal oxide in the mixed film and to grow the nano-crystals such that a part of the periphery of at least one of the nano-crystals is positioned within a distance of 0.7 nm from the interface of the insulating film, thereby obtaining a desired insulating film.

For achieving precipitation of the nano-crystalline metal oxide in the particular position within the mixed film, a mixed film containing TiO_2 and SiO_2 is formed first, followed by annealing the resultant mixed film in an Ar atmosphere of an atmospheric pressure. Alternatively, it is possible to apply the annealing treatment at a pressure higher than the atmospheric pressure, e.g., at a pressure higher than 100 kPa.

For forming the nano-crystals, it is desirable to apply the annealing treatment at an atmospheric pressure and the temperature falling within a range of

between 800℃ and 1,000℃. Alternatively, it is possible to apply the annealing treatment at a high pressure of about 10 MPa and temperatures falling within a range of between 600℃ and 1,000℃.

5　　　It is also desirable to form a thin film for preventing oxidation on the underlying substrate, e.g., a silicon substrate, before formation of the mixed film. To be more specific, it is desirable to form an oxynitride film by heat treatment using a NO

10　gas. If the oxidation preventing film sufficiently performs its function, it is possible to carry out the annealing treatment under high temperatures within an oxygen-containing atmosphere.

It is desirable to etch a part of the insulating

15　film, in which nano-crystals have been precipitated by heat treatment, so as to decrease the thickness of the insulating film to a desired level.

FIGS. 14A and 14B show C-V (capacitance-gate voltage) curves of the mixed layer containing the

20　nano-crystals thus formed. In this case, a SiO_2/TiO_2 mixed film having a thickness of about 3 nm, 5 nm or 10 nm was formed as an insulating film on an n-type silicon substrate. As shown in FIG. 14A, the hysteresis is diminished with a decrease in the

25　thickness of the film in the case where the SiO_2 content of the mixed film is 75%. In this case, the average grain diameter of the nano-crystals was found

to be about 2 nm. This indicates that, since the grain diameter of the nano-crystal is sufficiently smaller than the thickness of the mixed film, a recess of the energy level is formed in the vicinity of the crystal

5   grain, thereby trapping electric charge.

On the other hand, where the SiO_2 content was 26%, the hysteresis was scarcely recognized, as shown in FIG. 14B. The particular phenomenon is derived from the fact that the average grain diameter of the

10   nano-crystals was about 10 nm and, thus, the phenomenon as shown in FIG. 14A did not take place. Incidentally, where the film thickness is 3 nm or 5 nm, the size in the horizontal direction of the nano-crystal is about 10 nm. However, the size of the nano-crystal in

15   the thickness direction of the film is naturally substantially equal to the film thickness.

Example 5:

FIGS. 15A to 15E are cross sectional views collectively showing the manufacturing process of

20   the semiconductor device for Example 5.

Incidentally, FIGS. 15A to 15E are directed to an n-channel MOSFET. However, the present invention is not limited to the n-channel MOSFET. As a matter of fact, a p-channel MOSFET is also formed on the same

25   substrate, and the present invention is described herein later bearing in mind that the p-channel MOSFET is formed by the same process. Of course, the

technical idea of the present invention can be applied to an SOI (Silicon On Insulator) MOSFET and a vertical MOSFET in which the channel region extends in a direction perpendicular to the substrate surface and the electrons and holes are migrated in a direction perpendicular to the substrate surface.

In the first step, a SiO_2 film 131 for the trench element isolation is buried in a p-type silicon substrate 130, followed by depositing a TiO_2/SiO_2 mixed film 132 on the entire surface under temperatures at which crystallization does not take place, e.g., at room temperature, as shown in FIG. 15A. The mixed film 132 can be deposited by any of a vapor deposition method, an ordinary RF sputtering method, a sputtering method using a helical coil, a sol-gel method, a laser ablation method and a CVD method. Naturally, the temperature and the forming conditions of the mixed film 132 differ depending on the method of depositing the mixed film 132.

In the sputtering method using a helical coil, a target is prepared by finely pulverizing TiO_2 and SiO_2, followed by sintering the pulverized materials mixed at a predetermined mixing ratio. The mixing ratio of $Si/(Ti + Si)$ is set at 20%. After the target is positioned to face the silicon substrate, a sputtering was performed for 10 minutes under a mixed gas atmosphere of Ar and O_2 (Ar: 20 sccm;

O_2: 2 sccm) so as to deposit the mixed film 132 in a thickness of 5 nm. The sputtering was performed at room temperature with the power set at 100 W.

In the next step, a heat treatment was applied to the mixed film 132 at 800°C for 30 seconds under an Ar gas atmosphere so as to convert the mixed film 132 into a highly dielectric insulating film 133 containing nano-crystals, as shown in FIG. 15B. The heating conditions were controlled to permit most of the nano-crystals to have a grain diameter of about 5 nm in an attempt to realize the state shown in FIG. 13A. As a result, it was possible to avoid the problem that an electric charge was trapped in the insulating film. Also, if the heat treating temperature falls within a range of between 800°C and 1,000°C, it was possible to grow sufficiently large nano-crystals.

It is most desirable for all the nano-crystals to have a size substantially equal to the thickness of the film. However, it is not absolutely necessary for all the nano-crystals to have a size substantially equal to the thickness of the film. Even if nano-crystals having a small size are included, there is no problem if the amount of the small nano-crystals is small. To be more specific, it is possible to obtain a sufficient effect, if at least 50% by volume of the nano-crystals have a size substantially equal to

the thickness of the film. Incidentally, the volume

ratio of the nano-crystals having a size substantially

equal to the thickness of the film can be obtained by

measuring the size of each crystal and the distance of

the crystal from the interface of the insulating film

by TEM observation.

Alternatively, the grain diameter and frequency

of the crystals as well as the average thickness

of the insulating film are obtained by X-ray

diffractometry on the assumption that the crystals are

spherical (A. Benedetti et al., J. Appl. Cryst., 21

(1988), 543). The sum of the volume of the crystals

larger than the value obtained by subtracting 1.4 nm

from the thickness of the insulating film is obtained.

It is difficult to obtain the distance from the

interface of the insulating film for the individual

crystals. However, in order to allow a part of the

peripheral portion of at least one crystal smaller by

1.4 nm than the thickness of the insulating film to be

positioned at least 0.7 nm apart from the interface of

the insulating film, it is necessary for the crystal to

be positioned exactly in the center of the insulating

film. A part of the peripheral portion of a larger

crystal is positioned within 0.7 nm from the interface

of the insulating film without fail. Incidentally,

the hysteresis loop formed by the C-V curve is

substantially proportional to the number of trapped

electric charges. Where the electric charge is
trapped in only the portions of the crystal grains,
the amount of trapped electric charge is substantially
proportional to the volume of the crystal grains.
It follows that, if the total volume of the crystals,
a part of the peripheral portion of which is away from
the interface of the insulating film by a distance less
than 0.7 nm, is halved, the hysteresis is also halved,
with the result that an improvement of the MOSFET or
the like can be expected.

It is not absolutely necessary for the nano-
crystals to extend across the insulating film. As
shown in FIGS. 13B and 13C referred to previously, it
is possible for a thin SiO_2 film to be formed between
the edge portion of the nano-crystal and the surface of
the mixed film. Even in this case, if the thickness of
the SiO_2 film is not larger than 0.7 nm, the distance
from the interface of the mixed film is not larger than
0.7 nm in most of the microcrystals because the grain
diameter of the nano-crystal is sufficiently large.
It follows that the inconvenience of the trapped
electric charge is not generated.

In the next step, a patterned gate electrode 134
and a patterned highly dielectric insulating film 133
are obtained as shown in FIG. 15C. The gate electrode
134 and the highly dielectric insulating film 133 can
be formed, for example, as follows. In the first step,

a gate electrode containing, for example, a SiGe layer
134 is deposited in a thickness of 100 nm within a
mixed gas containing SiH_4 and GeH_4. Then, a resist
pattern is formed by lithography, and an acidic ion

5   etching is applied under an atmosphere of CF_4 and O_2
with the resultant resist pattern used as a mask so as
to process the SiGe film 134 into the shape of the gate
electrode. After the acidic ion etching step, the
highly dielectric insulating film 133 including nano-

10   crystals is processed with a solution containing HF.

In the next step, arsenic ions are implanted
into the p-type silicon substrate 130 at a dose of
1×10^{14} cm^{-2} under an accelerating energy of 300 eV.
In this ion implantation step, the patterned gate

15   electrode 134 and the patterned highly dielectric
insulating film 133 are used as a mask. Further, a SiN
film is deposited on the entire surface, followed by
applying RIE etching to the entire surface so as to
form a gate side wall SiN film 135 in a thickness of

20   10 nm, as shown in FIG. 15D. Still further, arsenic
ions are implanted again at a dose of 1×10^{15} cm^{-2}
and under an accelerating energy of 10 keV with the
SiGe film 134 and the side wall SiN film 135 used as
a mask. After the ion implantation step, RTA (rapid

25   temperature annealing) is applied at 900°C for
30 seconds so as to form source-drain regions 136a,
136b and add an n-type impurity to the SiGe film 134

forming a gate electrode.

In the next step, a $CoSi_2$ film 137 is deposited on the source region, the drain region and the gate electrode by the deposition of cobalt, heat treatment and etching. Finally, a SiO_2 film 138 forming an interlayer insulating film is deposited on the entire surface by using, for example, TEOS, followed by forming a wiring layer 139 of an Al/TiN/Ti structure or a Cu/TiN/Ti structure in a manner to fill the contact holes connected to the source-drain regions. In the subsequent process, the wiring step for the second layer et seq. is carried out so as to finish the manufacture of an LSI.

In the semiconductor device thus manufactured, the nano-crystals contained in the highly dielectric insulating film 133 forming the gate insulating film have a diameter of about 5 nm and, thus, substantially extend through the upper and lower surfaces of the insulating film 133. It follows that the trapping energy level as shown in FIG. 12 referred to previously is not generated, making it possible to suppress the nonuniformity in the threshold value and the driving force. As a result, the characteristics of the MOS transistor, etc. can be improved.

In this Example 5, nano-crystals in the highly dielectric insulating film 133 are formed immediately after depositing the mixed film. However, it is

possible to form the nano-crystals after depositing the gate electrode or after patterning the highly dielectric insulating film. Alternatively it is also possible to form the nano-crystals during activating the impurity doped in the semiconductor substrate.

Example 6:

Example 6 is directed to an improvement of the annealing method of the mixed film in Example 5 described above.

Specifically, a TiO_2/SiO_2 mixed film 132 was deposited by the method similar to that employed in Example 5 under temperatures at which crystallization did not take place, e.g., under room temperature. Then, a heat treatment was applied at 600°C for 30 seconds under a high pressure of 10 MPa so as to form a highly dielectric insulating film containing nano-crystals. It was possible to form nano-crystals having a grain diameter of about 5 nm in this case, too, as in Example 5. Further, the steps shown in FIGS. 15C to 15E were performed as in Example 5 so as to finish the manufacture of an LSI.

According to Example 6, it is possible to form nano-crystals having a diameter of about 5 nm in the mixed film 132 such that the nano-crystals extend across the insulating film, making it possible to obtain the effects similar to those obtained in Example 5. In addition, Example 6 produces an effect

that, since the heat treatment is carried out under
a high pressure, it is possible to carry out the
annealing for preparation of the nano-crystals under
a lower temperature. According to the experiment

5   conducted by the present inventors, it is possible to
form the nano-crystals required in Example 6 of the
present invention by the heat treatment carried out
under temperatures falling within a range of between
$600°C$ and $1,000°C$ if the heat treatment is carried out

10 under the pressure of 10 MPa.
Example 7:

Example 7 is directed to an improvement in the
method of forming the mixed film employed in Example 5
described previously.

15 Specifically, a TiO_2/SiO_2 mixed film 132 was
deposited by the method similar to that employed in
Example 5 under temperatures at which crystallization
did not take place, e.g., under room temperature.
In Example 7, however, the mixed film 132 was deposited

20 in a large thickness of 100 nm. Then, a heat treatment
was applied at $800°C$ for 30 seconds under an Ar gas
atmosphere so as to convert the mixed film into
a highly dielectric insulating film containing TiO_2
nano-crystals. It was possible to form nano-crystals

25 such that a majority of the formed nano-crystals had
a grain diameter of about 5 nm in this case, too, as in
Example 5.

Then, the thickness of the highly dielectric
insulating film 133 was decreased to 5 nm by the
treatment with a solution containing HF, e.g., a mixed
solution containing 1 part of a 47% HF and 10 parts of
5   H_2O, for 5 minutes. The etch back step of the highly
dielectric insulating film can also be applied to
the case other than the case where the etch back is
performed uniformly over the entire surface. It is
possible to apply the etch back to only a part, e.g.,
10   to only the p-channel MOS, to only the portion where
the threshold voltage is partially changed, to only
the portion corresponding to the logic SLI in a mixed
LSI, or to only the portion corresponding to the memory
LSI. Further, the steps shown in FIGS. 15C to 15E
15   were performed as in Example 5 so as to finish the
manufacture of an LSI. In this Example 7, it is also
possible to decrease the thickness of the highly
dielectric insulating film before heat treatment for
forming nano-crystals.

20   According to Example 7, it is possible to form
nano-crystals having a diameter of about 5 nm in the
mixed film 132 such that the nano-crystals extend
across the insulating film, making it possible to
obtain the effects similar to those obtained in
25   Example 6.

Example 8:

In Example 8, an oxynitride film (not shown)

having a thickness of 0.7 μm is formed on the silicon

substrate 130 by the heat treatment at 850℃ for

5 seconds using a NO gas before formation of the mixed

film that is to be converted into the gate insulating

5   film. Then, as in Example 5, a TiO_2/SiO_2 mixed film

132 is formed in a thickness of 5 nm on the oxynitride

film. Further, the steps shown in FIGS. 15C to 15E

are performed as in Example 5 so as to finish the

manufacture of an LSI.

10   According to Example 8, it is possible to form

nano-crystals having a diameter of about 5 nm in the

mixed film 132 such that the nano-crystals extend

across the insulating film, making it possible

to obtain the effects similar to those obtained in

15   Example 5. Also, in Example 8, an oxynitride film is

formed on the silicon substrate 130 before formation of

the TiO_2/SiO_2 mixed film 132, with the result that,

even if the mixed film 132 is formed and annealed under

an oxygen-containing atmosphere, it is possible to

20   suppress the diffusion of oxygen into the substrate.

Example 9:

        The present invention is not limited to each of

the Examples described above. These Examples can be

employed singly or in combination. It is also possible

25   combine the Examples described above with the method

described below.

        Specifically, the mixed film can be formed as

follows. In the first step, a Ti layer is formed on a clean silicon substrate by, for example, a sputtering method, a vapor deposition method, a CVD method or a plasma CVD method, followed by annealing the substrate under an inert atmosphere so as to form a titanium silicide layer on the substrate. Then, it is possible to peel of the unreacted Ti. Further, an annealing treatment is applied under an oxygen-containing atmosphere. It is possible for the oxygen-containing atmosphere to contain H_2O, and O_3 as well as O, N and OH in the state of plasma. Since Ti is readily oxidized, it is possible to apply the annealing treatment under the air atmosphere or under an atmosphere containing at most 10 kPa of the oxygen partial pressure at 100℃ or less. Then, an additional annealing treatment is applied at 800℃ under an Ar gas atmosphere so as to precipitate nano-crystals.

Further, it is possible to form a Ti layer under an oxygen-containing atmosphere so as to oxidize Ti at least partially. It is also possible to form a Ti layer on a silicon oxide film, followed by applying an annealing treatment so as to oxidize Ti at least partially. Further, an oxidation is performed, as required, followed by performing an annealing treatment so as to precipitate nano-crystals.

It is possible to form a mixed film containing a suitable combination of Ti, Si, a compound between Ti

and Si and an oxide of at least one of these materials
by a simultaneous sputtering method or a vapor
deposition. It is not absolutely necessary to form the
mixed film by a single deposition. It is also possible
to form the mixed film by depositing several times
a film having the same or different mixing ratio under
the same or different atmospheres. Then, the oxidation
is performed as required, followed by performing the
annealing treatment so as to precipitate nano-crystals.

In each of the Examples described above, TiO_2
nano-crystals were formed in the insulating film.
However, the nano-crystals formed in the insulating
film are not limited to TiO_2 nano-crystals. A similar
method can be applied even in the case where an
amorphous layer having an energy level lower than
the surrounding energy level is precipitated.

In each of the Examples described above, TiO_2 is
contained as one of the components of the mixed film
forming the insulating film. Alternatively, it is also
possible to use an oxide, a nitride or an oxynitride of
Ta, Y, Al, Zr, La, Hf, Nb or lanthanum series element
such as La, Ce, Pr, Nd, Pm, Sm, Eu, Gd, Tb, Dy, Ho, Er,
Tm, Yb and Lu in place of TiO_2. It should be noted,
however, that the temperature at which nano-crystals
are formed depends on the material. As the substrate
for forming the insulating film of the present
invention, it is required to use a surface not having

a crystallinity. Alternatively, it is important to use the surface formed of a material having a large lattice mismatch with the metal oxide thereof. Otherwise, the crystal growth occurs preferentially from the

5   substrate, resulting in failure to form nano-crystals. Of course, where Si(100) has a large lattice mismatch with the metal oxide thereof, it is possible to form the mixed film directly without worrying about the crystal growth.

10   The other component of the mixed film is not limited to SiO_2. It is also possible to use SiON or SiN in place of SiO_2. It should be noted, however, in the combination forming a conductive material such as TiN, it is naturally impossible to use SiN in

15   combination with the other component such as TiN, though it is possible to use SiON in combination with, for example, TiN.

It is possible to use a material having a low resistivity such as Ag for forming the wiring.

20   Further, it is possible to use, for example, TiSiN, WSiN or TaSiN for forming the underlying layer. It is also possible to bury W, NiSi, Al or Cu in the contact hole.

Further, a CoSi film is formed by a salicide

25   process on the SiGe film used as the gate electrode. Alternatively, it is possible to deposit, for example, WSi_2 on the entire surface immediately after deposition

of the SiGe film. It is possible to lower the resistivity of the gate by processing, for example, the WSi_2 film deposited on the entire surface. Also, the TiSiO film is deposited by a single depositing operation. However, it is of course possible to carry out the depositing operation several times by changing the mixing ratio.

In each of the Examples described above, SiGe was used as the material of the gate electrode. Alternatively, it is also possible to use polysilicon, a metal or a combination of a metal and a metallic silicon side gate material for forming the gate electrode.

In each of the Examples described above, the extension of the source-drain regions, i.e., the shallow junction portion below the SiN side wall, is formed by ion implantation alone. However, it is also possible to form a silicon layer on the substrate in a thickness of about 20 nm by a selective CVD method on the source-drain regions by using, for example, SiH_4, followed by applying an ion implantation. In this case, the accelerating energy in the ion implantation step can be increased to, for example, 10 keV so as to improve the ion implantation efficiency.

Each of the Examples described above is directed to a MOS transistor. However, it is possible to apply the technical idea of the present invention to various

semiconductor devices using a highly dielectric insulating film including, for example, a MOS capacitor. Further, as already described in conjunction with Example 1, the technical idea of the present invention can be applied to a MOSFET of SOI structure and to a vertical MOS devices. Further, various modifications are available within the technical scope of the present invention.

As described above in detail, the present invention provides a semiconductor device, which permits suppressing the leakage current derived from the grain boundary, permits suppressing the nonuniformity in the threshold value and the driving force, and further permits improving the characteristics of the MOS transistor, etc. and a method of manufacturing the particular semiconductor device.

The present invention also provides a semiconductor device, which permits suppressing the leakage current derived from the crystal grain boundary, permits eliminating the trap of the charge within the film so as to suppress the nonuniformity in the threshold value and the driving force, and is effective at improving the characteristics of a MOS transistor, etc., and a method of manufacturing the particular semiconductor device.

To reiterate, the present invention can be highly

effectively applied to a semiconductor device using a highly dielectric thin film and, thus, is prominently valuable in industry.

Additional advantages and modifications will readily occur to those skilled in the art. Therefore, the invention in its broader aspects is not limited to the specific details and representative embodiments shown and described herein. Accordingly, various modifications may be made without departing from the spirit or scope of the general inventive concept as defined by the appended claims and their equivalents.